



LE SPÉCIALISTE EN TOILES ET FILETS

FABRENE W130N9N9

Made from high density polyethylene tapes, coated on both sides with low density polyethylene. This product is UV stabilized.

PROPERTY	UNIT	VALUES	TEST METHOD
Unit weight	Oz / square yard	6.8	ASTM D3776
Warp construction	Tapes/in Warp	12.2	ASTM D 3775
	Tapes/in Welt	8.1	
width	inches	Up to 144	
Tensile grab	lbf Warp	292	ASTM D751
	lbf Welt	270	
Tear strenght (tongue)	lbf Warp	84	ASTM D2261
Include force to shift tapes	lbf Welt	84	
Tear may be crosswire to direction of force			
Coating	mil Natural	2	ASTM D1777 MOD
Mullen Burst Strenght	psi	392	ASTM D751
Water Vapour Transmission	US Perms	-1	ASTM E96 A

This product contains ultraviolet inhibitors and is suitable for prolonged outdoor exposure

Mégatex inc.

2800 rue Dalton, suite 1, Québec (Ste-Foy) Qc. G1P 3S4

Tél. : (418) 651-2800 Fax : (418) 651-6755

Courriel : info@megatex.ca

ventes@megatex.ca