



LE SPÉCIALISTE EN TOILES ET FILETS

TECHNICAL DATA SHEET

H 1850

Product code : H 1850_61100

H 1850_73100

BASE FABRIC

Weight of base fabric	5oz psy	
Denier of fabric	1300/1000 denier	
Fabri count	17 warp / 18 weft	

Using higher denier in the warp increases tear strength in the weft direction hence making both weft and warp of equal tear strength

Note that 20 V 20 weave (1000D) has a theoretical 5.2 oz. base

COATED FABRIC

Overall weight	18.5 oz. psy	
Type of coating	PVC (polyvinyl Chloride)	
Coating distribution	40 / 60	
Colors in stock	White/Black/Blue/Green/Red/ Burgundy / Yellow/ Tan / Orange / Brown	
Width of fabric	61 " X 73 "	
Sealing properties	Dialetric & Thermal	

MECHANICAL PROPERTIES

Tensile (grab)	444 / 441	FS 191 Method FS5134
Adhesion	17 lb / 2"	FS 191 Method 5970
Tongue Tear	81 Warp / 85 Weft	ASTM D751-79
Low cold crack	-40 C	Fed Method 5874

We believe this information is the best currently available on the subject. We make np guarantee of result and assume no obligation or liability in connection with this information.

Mégatex inc.

2800 rue Dalton, suite 1, Québec (Ste-Foy) Qc. G1P 3S4

Tél. : (418) 651-2800 Fax : (418) 651-6755

Courriel : info@megatex.ca

ventes@megatex.ca