



LE SPÉCIALISTE EN TOILES ET FILETS

## TECHNICAL DATA SHEET

### MEGATEX 1455 POLY FR U.V.I.

**Description:** High density polyethylene woven fabric base complete with a low density coating

		<b>Test method</b>
<b>Denier of tape</b>	1000 D	
<b>Construction</b>	Warp 14, Weft 14	
<b>weight</b>	6 oz. per sq. yard	
<b>Tensile grab strength</b>	Warp 155	ASTM D-1682
	Weft 170	ASTM D-1682
<b>Grab tear</b>	Warp 30	ASTM D-2261
	Weft 25	ASTM D-2261
<b>Burst</b>	280 PSI	
<b>Thickness (overall)</b>	12 mil	
<b>Ultraviolet treated</b>	2000 hr at 50%	
<b>Roll width</b>	72 "	
<b>Color</b>	White	
<b>Weatherability</b>	Special treatment gives 50% retention after 200 hours in a weatherometer	
<b>Fire retardant (intl)</b>	2 sec self ext.	CPAI 84 section 5
<b>Fire retardant (Canada)</b>	Small flame test	CAN / ULC-S109
<b>Fire Retardant ( Canada)</b>	Large Flame Test	CAN / ULC-S109
<b>Fire Retardant (USA)</b>		NFPA 701

We believe this information is the best currently available on the subject. We make no guarantee of results and assume no obligation or liability in connection with this information. It is offered as possible helpful suggestion in any experimentation you may care to undertake these lines.

#### **Mégatex inc.**

2800 rue Dalton, suite 1, Québec (Ste-Foy) Qc. G1P 3S4

Tél. : (418) 651-2800 Fax : (418) 651-6755

Courriel : [info@megatex.ca](mailto:info@megatex.ca)

[ventes@megatex.ca](mailto:ventes@megatex.ca)