



LE SPÉCIALISTE EN TOILES ET FILETS

July 2018

TECHNICAL DATA SHEET

CLEAR SPAN FR

		TEST METHOD
Fiber of base	Polyester	
Type of coating	Laminate	
Treatment of tarps	Anti wicking Anti-mildew	
Treatment of coating	UV resistant Yellowing Prevention Hi-Gloss (easy to clean)	
Width of Fabric	61"	
Roll lenght	100 yards	
Weight	14 oz/ yd ²	
Color	Clear only	
Tear	Warp 30 Fill 30	Federal Method 5134
Tensile (grab)	Warp 140 Fill 125	Federal Method 5100.1
Hydrostatic resistance	200 psi	Federal Method 5122
Flame resistance	< 2 sec. self extinguish < 6 char length	Federal Method 5903
Cold resistance	-30° F	Federal Method 5874

We believe this information is the best currently available on this subject. We make no guarantee or results and assume no obligation or liability in connection with this information. It is offered only as possible helpful suggestion in any experimentation you may care to undertake along these lines

Mégatex inc.

2800 rue Dalton, suite 1, Québec (Ste-Foy) Qc. G1P 3S4

Tél. : (418) 651-2800 Fax : (418) 651-6755

Courriel : info@megatex.ca

ventes@megatex.ca